

PVC Heat Shrink Tubing

Property	Test Method	Typical Value
Specific Gravity	ASTM D 792	1.32
Durometer Shore A		
Instantaneous		93
10 Seconds		88
Tensile Strength	ASTM D 2671	3,000 psi
Ultimate Elongation	ASTM D 2671	300%
Brittleness Temperature	ASTM D 746	-28°C
Heat Aging		
7 days @ 136°C	UL Subject 224	
Retention of Tensile		102%
Retention of Elongation		95%
Flammability	UL Subject 224 VW-1	Pass
Deformation 1 hour @ 121°C	UL Subject 224	22%
Volume Resistivity	ASTM D 257	.065
Dielectric Strength	ASTM D 149	1,083 vpm

HeatShrinkTubingDirect.com